

Compound	Unidure DD70	Unidure DD65	Unidure DD60
Hardness	70D	65D	60D
Rebound	60	52	52
Tensile	7200	6400	6400
100% Mod	4600	3250	3250
300% Mod	5800	NA	NA
Elongation	265	300	300
DieC Tear	905	620	620
Split	205	160	160
CompSet	NA	30	30
Backbone	Polyether	Polyether	Polyether