

Compound	Unidure D70	Unidure D65	Unidure D60
Hardness	70D	65D	60D
Rebound	52	55	55
Tensile	6650	5000	5000
100% Mod	4460	3700	3700
300% Mod	NA	NA	NA
Elongation	240	275	275
DieC Tear	1100	775	775
Split	175	160	160
CompSet	NA	NA	NA
Backbone	Polyether	Polyether	Polyether