

Compound	Unidure AME95	Unidure AME90	Unidure AME85
Hardness	95A	90A	85A
Rebound	50	50	45
Tensile	7200	7200	7150
100% Mod	1075	1075	800
300% Mod	2400	2400	1660
Elongation	570	570	680
DieC Tear	625	625	525
Split	330	330	310
CompSet	21	21	24
Backbone	Polyester (MDI)	Polyester (MDI)	Polyester (MDI) *Dry food