

Compound	Unidure AM95	Unidure AM90	Unidure AM85	Unidure AM75
Hardness	95A	90A	85A	75A
Rebound	60	66	69	75
Tensile	5800	5500	5000	4350
100% Mod	1270	1050	825	650
300% Mod	2200	1800	1560	1300
Elongation	600	555	555	550
DieC Tear	600	485	430	350
Split	180	90	60	40
CompSet	20	22	17	18
Backbone	Polyether (MDI)	Polyether (MDI)	Polyether (MDI)	Polyether (MDI)